

## EX-TECH EX-ALLOY 3000 RPET EXTRUDED SHEET

### TECHNICAL DATA

Physical Property	Typical Value	Units	ASTM Test Method
Specific Gravity	1.33	g/cm3	
Shrinkage	2.0 – 5.0	%	D 955
Tensile Strength @ Yield	7 – 8,000	psi	D 638
Flexural Modulus	300 – 350,000	psi	D 790
Ultimate Elongation	100 – 200	%	D 638
Intrinsic Viscosity (IV)	> 0.65		D 3835
Light Transmission	> 85	%	D 1003
Haze ( $\leq$ .020" sheet)	$\leq$ 10	%	D 1003
Clarity	> 97	%	D 1003

Information contained herein is considered accurate to the best of our knowledge. It is offered for your consideration and investigation. No warranty is made or implied.

#### Ex-Tech Value-Added Services

- Sheeting
- Slitting
- Laminating
- Coating
- Corona Treating
- Special Packaging Services
- Warehousing



11413 Burlington Road, Richmond, IL 60071  
TEL 847.829.8100 FAX 847.829.8190