

EX-TECH EX-ALLOY 3100 PRIME APET EXTRUDED SHEET

TECHNICAL DATA

| Physical Property | Typical Value | Units | ASTM Test Method |
|--------------------------|---------------|-------|------------------|
| Specific Gravity | 1.33 | g/cm3 | |
| Melting Point | 240 min. | deg C | |
| Shrinkage | 2.0 – 5.0 | % | D 955 |
| Tensile Strength @ Yield | 8500 | psi | D 638 |
| Flexural Modulus | 350,000 | psi | D 790 |
| Ultimate Elongation | 250 | % | D 638 |
| Intrinsic Viscosity (IV) | > 0.75 | | D 3835 |
| Light Transmission | > 90 | % | D 1003 |
| Haze | < 2 | % | D 1003 |
| Clarity | > 99 | % | D 1003 |

Ex-Alloy 3100 complies with all applicable portions of 21CFR177.1630 of the Food and Drug Administration.

Information contained herein is considered accurate to the best of our knowledge.
It is offered for your consideration and investigation. No warranty is made or implied.

Ex-Tech Value-Added Services

- Sheeting
- Slitting
- Laminating
- Coating
- Corona Treating
- Special Packaging Services
- Warehousing



11413 Burlington Road, Richmond, IL 60071
TEL 815.678.2131 FAX 815.678.4248