



# DURATECH HIGH DENSITY POLYETHYLENE 9000 HDPE EXTRUDED SHEET

## Technical Data

Physical Property	Typical Value	Units	ASTM Test Method
Specific Gravity	.964	g/cm <sup>3</sup>	D 1505
Melt Mass-Flow Rate (MFR)	.65	g/10 min	D 1238
ESCR	10.0	hr	D 1693B
Tensile Strength @ Yield	4,400	psi	D 638
Flexural Modulus	240,000	psi	D 790
Ultimate Elongation	>300	%	D 638
Brittleness Temperature	< -180	deg F	D 746

- Typical properties: These are not to be construed as specifications.

DURATECH HIGH DENSITY POLYETHYLENE 9000 HDPE complies with all applicable portions of 21CFR177.1520 of the Food and Drug Administration. Information contained herein is considered accurate to the best of our knowledge. It is offered for your consideration and investigation. No warranty is made or implied.

DURATECH HDPE 9000 is also available in white, black and custom colors.

### Ex-Tech Value-Added Services

- Sheeting
- Laminating
- Coating
- Corona Treating
- Special Packaging Services
- Warehousing

