

## VERSATECH 3100 PRIME APET EXTRUDED SHEET

### Technical Data

Physical Property	Typical Value	Units	ASTM Test Method
Specific Gravity	1.33	g/cm <sup>3</sup>	
Melting Point	240 min.	deg C	
Shrinkage	2.0 – 5.0	%	D 955
Tensile Strength @ Yield	8500	psi	D 638
Flexural Modulus	350,000	psi	D 790
Ultimate Elongation	250	%	D 638
Light Transmission	> 90	%	D 1003
Haze	< 2	%	D 1003
Clarity	> 99	%	D 1003

VERSATECH PET 3100 PRIME APET complies with all applicable portions of 21CFR177.1630 of the Food and Drug Administration. Information contained herein is considered accurate to the best of our knowledge. It is offered for your consideration and investigation. No warranty is made or implied. VERSATECH PET 3100 PRIME APET is also available in white, black and custom colors.

### Ex-Tech Value-Added Services

- Sheeting
- Slitting
- Laminating
- Coating
- Corona Treating
- Special Packaging Services
- Warehousing

